



COPRABEL
Quality in Colors

COPRABEL S.A Z.I. Wavre-Nord, Avenue Lavoisier, 7
BE-1300 Wavre Belgium
Tel: +32 10 23 82 80 Fax:+32 10 23 82 89
www.coprabel.com info@coprabel.com



TECHNICAL DATA SHEET

NARI® WOOD STAIN (various colors)

DESCRIPTION

NARI® WOOD STAIN is a ready-to-use, solvent-based tinting penetrating dye for the decoration of all types of new wood, with UV resistant coloring agents which penetrate regularly into the wood. It is suitable for indoor and outdoor use.

It can be applied on various surfaces: doors, tables, chairs, frames, rails, banisters, baseboards, furniture, etc. It has the property of avoiding the peeling of wood fibers and is compatible with all types of sealers and lacquers. They are available in 20 different colors that can be mixed together.

These stains offer a high coverage that can be overcoated with NARI® N.C. Lacquer or with NARI® 2K PU available in gloss, satin and matt according to the required effect (a matt top coat will decrease the brilliance of the stain).

PRECAUTIONS

- Mix carefully before use.
- Avoid contact with eyes and skin.
- Wear protective clothes, glasses and gloves.
- Keep out of reach of children.
- Do not dispose of residual paint by flushing it away.
- Take the appropriate precaution when disposing of the packages.
- Consult the Safety Data Sheet for more details.



COPRABEL
Quality in Colors

COPRABEL S.A Z.I. Wavre-Nord, Avenue Lavoisier, 7
BE-1300 Wavre Belgium
Tel: +32 10 23 82 80 Fax: +32 10 23 82 89
www.coprabel.com info@coprabel.com



TECHNICAL DATA SHEET

NARI® WOOD STAIN (various colors)

METHOD OF USE

Surface preparation	Surface must be dry, clean and free of dirt, grease, glue and existing coatings before staining. Sand the wood in the direction of the grain using fine-grade sandpaper until smooth. Remove all sanding dust.
Application	Ready to use. Stir thoroughly before and while using. Can be applied by brush, airless pistol, stamping and by dipping. <ol style="list-style-type: none">1. Apply stain in the direction of the grain with a brush or clean cloth. Remove stain that has not penetrated the wood with a clean cloth. Wipe in the direction of the grain, while blending light and dark areas to obtain uniform color. DO NOT ALLOW STAIN THAT HAS NOT PENETRATED THE WOOD TO DRY ON THE WOOD SURFACE.2. Apply NARI® Sanding Sealer3. Apply as a top coat NARI® Lacquer or NARI® 2K PU.
Drying time	20°C 60% HR and 50 µm dry. Dust free: 20 min.
Recoatable	After 1 hour. Slightly sand before applying the second coat.
Cleaning of material	Clean using cleansing agents. Do not use solvents.
Shelf life	5 years in the non-open original packaging.

TECHNICAL SPECIFICATIONS

Aspect	Liquid.
Composition	Binder: none. Pigments: Colorants. Solvent: butanone, acetone, aromatic hydrocarbons.
Solid content	Varies according to the tint. Cfr. corresponding MSDS.
Density at 20°C	Varies according to the tint. Cfr. corresponding MSDS.
Flash point	Varies according to the tint. Cfr. corresponding MSDS.
Coverage	10-18 m ² /L on clean and dry wood (depends on the type of wood).
Packaging	1 L – 3,5 L.



COPRABEL
Quality in Colors

COPRABEL S.A Z.I. Wavre-Nord, Avenue Lavoisier, 7
BE-1300 Wavre Belgium
Tel: +32 10 23 82 80 Fax: +32 10 23 82 89
www.coprabel.com info@coprabel.com



TECHNICAL DATA SHEET

NARI® WOOD STAIN (various colors)

REMARKS AND RECOMMENDATIONS

Store in a well-ventilated and dry room at temperatures between 15 °C and 30 °C. Higher temperature could have a significant influence on drying time. Relative humidity of the environment: <80%. Protect from heat and direct sunlight. Keep container tightly closed. Store carefully closed containers upright to prevent any leaks.

For a long-lasting effect, apply after 24 hours the protective clear finish NARI ® 2K PU as topcoat or NARI® N.C. Lacquer.

Warranty invalid, if other system than provided by COPRABEL S.A. is used.

Note: Cancels and replaces the former editions. It's up to our customers to check, before application, if it is indeed the latest edition. The information contained in this note has only one indicative range and cannot compensate a description suitable with the nature and the state of surface to be treated.